

Grading Rules for Australian Oak Engineered Flooring

AUSTRALIAN OAK DETAILS

190X15/4 x1.9m

8 pieces per pack – 2.888m² (20% shorts)

Micro bevel all edges

Hardwood ply construction

Back sawn (crown cut)

GRADE RULES

Up to 5% leniency allowed for human error.

Select Grade

- End split or gum vein to be up to 200mm long maximum aggregate length
- Multiple gum vein or split allowed if add up to less than 200mm combined. Not to have multiple defects if add to more than 200mm
- Knots not allowed

Feature Grade

- Knots allow if filled
- Gum vein allowed
- End splits allowed if filled



Select grade – sleek & clean appearance, doesn't contain a lot of natural markings in gum vein or knots.



Feature grade – natural character and markings will occur throughout this grade.

The above images are an example only and the viewer should expect their floor to vary. Every characteristic listed above will be possible in your floor.